

# DIGUN

- General purpose gunning refractory for hot face lining construction refractory mix specially formulated for rapid firing.

Grade	Maximum Service Temperature	Material Required	Chemical Analysis, %				Remarks
	°C	kg/m <sup>3</sup>	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	
DIGUN 150 VG	1500	2000	56	33.9	0.76	6.9	1500°C gunning mix, specially for rapid firing applicable for hot-face lining construction